

Calidad	Espesor (mm)	R _e (MPa)	R _m (MPa)	A ₈₀ (%)	C (%)	Mn (%)	P (%)	S (%)
<i>HC180 AM FCE</i>	0.5 - 3	180 - 280	300 - 360	≥ 32	≤ 0.120	≤ 0.60	≤ 0.030	≤ 0.025
<i>HC200 AM FCE</i>	0.5 - 3	200 - 300	310 - 370	≥ 31	≤ 0.130	≤ 0.60	≤ 0.030	≤ 0.025
<i>HC220 AM FCE</i>	0.5 - 3	220 - 280	320 - 380	≥ 28	≤ 0.120	≤ 0.70	≤ 0.045	≤ 0.025